

Sub 100
high index layer, having a refractive index of at most 2.3, and (c) the layers of low refractive index have a refractive index of between 1.30 and 1.65.

Sub 100
B2
14. (Amended) The transparent substrate of claim 1, wherein the low index thin layers comprise one or more of silicon oxide, aluminum oxide, aluminum oxyfluoride, aluminum fluoride, and magnesium fluoride, wherein the oxides are optionally halogenated.

BEST AVAILABLE COPY